



TECHNICAL DATA SHEET

SUPER POLYURETHANE WOOD STAIN **PENETRATING WOOD STAIN**

PRODUCT

DESCRIPTION: A special formulation of extra-tough polyurethane and natural wood stain color for a one-step-application on interior wood surfaces. This polyurethane finish protects against wear, abrasion, alcohol, water and household chemicals. When dry, lead-free formula is safe for children's furniture.

BASIC USES: Seal new or previously stained wood on interior wood surfaces. Quickly renews old, dull and worn surfaces such as furniture, doors, woodwork, cabinets. Recommended for floor only when high traffic areas are covered with rugs or carpets. As with all coatings used on floors, normal wear will eventually show. To further protect, a topcoat of *Lanco® Clear Polyurethane* may be applied.

PRODUCT

ADVANTAGES:

* Non Yellowing	* Lead Free
* Will not bleed	* Fast Drying
* Tough and Flexible	* Extremely Durable

COLORS: Available in eight (8) beautiful colors.

TECHNICAL DATA

Percent Solid:	50.00 ± 1% by weight 45.00 ± 1% by volume	Finish:	Satin
Weight / Gallon:	7.36 ± 0.5 lbs.	Viscosity:	120 –150 cps.
Drying Time:	To touch: 4 hours To recoat: 12 hours	Theoretical Coverage:	600 sq. ft. / gal.
Flash Point:	< 20°F TOC	Sizes:	1 gallon 1 quarts
Recommended Film Thickness:	2 mils dry, 4 mils wet		
Thinning:	Not normally recommended, but if necessary, add up to 1/2 pint per gallon of <i>LANCO® Mineral Spirits MS-107</i> .		

Surface Preparation: All surfaces must be dry, clean and free of contaminants such as dirt, grease, chalk, mildew, oil, rust, loose or badly cracked paint.

New Wood: Sand down to a smooth finish with fine sandpaper following the grain. Remove all sanding dust by vacuuming or dusting the surface with a "tack" cloth. Fill knot holes and cracks with *LANCO*[®] putty filler for wood; let dry. Sand the filled areas smooth and remove dust.

Previously Painted Surfaces: This coating is for application to unfinished wood surfaces or to surfaces previously finished with this same finish and in good condition. If the previous finish is not in good condition it must be completely removed with *LANCO*[®] *Safe Strip*[™] *PR-113*. Finish the surface as in *New Surfaces*. If surface is in good condition, sand to remove gloss and touch-up bare areas with this same product. If doubt exists concerning compatibility of this coating with the previous system, apply coating to a small area (25 square feet minimum) and allow to cure and age several weeks. Then inspect for adhesion failure, wrinkling, lifting or any other sign of incompatibility. If there are no signs, coating work can proceed.

Mixing: This is a one component coating. Always hand mix thoroughly with a paddle before application. Do not mix excessively to avoid air in the coating.

Application: Apply by brush, spray or rag generously in the direction of the grain.

Equipment: Conventional Spray: For suction feed, use DeVilbiss MBC gun with "E" tip and needle and 30 air cap or equivalent at 35-40 psi atomizing pressure feed. For pressure feed, use DeVilbiss MBC gun with tip and needle and 704 air cap or equivalent at 35-40 psi atomizing pressure and 5-8 psi fluid pressure, 3/8" ID material hose, double regulated pressure tank with oil and moisture separator. Airless Spray: Minimum of 28:1 ratio pump, .011"-0.013" orifice tip 1/4" ID Teflon material hose.

Limitation: Apply in good weather when air and surface temperature are above 40°F and surface temperature is at least 5°F above the dew point. For optimum application properties, material should be between 70° to 100°F prior to mixing and application.

Note: When multiple coats of product are applied, be sure to sand lightly between coats with a fine sandpaper and dust clean or vacuum.

Cleanup: Wipe up drips and spatters with *LANCO*[®] *Mineral Spirits MS-107*. Clean all equipment with this solution.

Caution: Do not take internally. Close container after each use. Keep out of the reach of children. *Combustible; keep away from heat and open flame*. Avoid prolonged contact with skin and breathing vapors or spray mist.

Notice: The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.

M.S.D.S.: Available upon request.