



PATCHING PLASTER

PP-223

WHITE PATCHING PASTE

PRODUCT

DESCRIPTION: A ready-to-use, white patching paste to fill and repair cracks and holes in plaster, drywall and wood surfaces; dries quickly, sands easily and will not shrink.

BASIC USES: Excellent for the repair of nail holes, cracks and dents in drywall, plaster, wood, brick, stone, concrete and other interior surfaces.

PRODUCT

ADVANTAGES:

* Anti-fungus	* Ready mixed
* Easy to apply	* Dries hard
* Water cleanup	* Fast-drying
* Easy to sand	* White finish

TECHNICAL DATA

Percent Solids:	63.00 ± 1% by weight 42.00 ± 1% by volume	Finish:	White
Texture:	Smooth	Viscosity:	350,000-400,000 cps
Weight / Gallon:	13.24 ± 0.5 lbs.	Percent Pigment by Weight:	63.00 ± 1%
Flash Point:	Non-flammable		
Drying Time:	To touch: 30 minutes To sand: 1 hour To coat with latex paint: 2 hours To coat with alkyd paint: 24 hours	Sizes:	1 gallon 1 quart 1 pint 8 ounces
Theoretical Coverage:	Depends on depth and size of holes and cracks		

Surface Preparation: Surface to be filled must be dry, clean and free of contaminants such as dirt, grease, chalk, dust, wax, loose paint or plaster.

Application: For best results, follow these instructions:

- (1) Rough smooth surfaces with sandpaper before application.
- (2) Apply *LANCO® Patching Plaster PP-223* with putty knife. One fill is usually sufficient for small dents and holes.
- (3) For deep fills, apply two or more layers, allowing *LANCO® Patching Plaster PP-223* to dry between applications.
- (4) Can be sanded or painted two hours after application. Allow longer drying time for deep fills.

Limitation: Do not apply in exterior surfaces. Do not use as caulk, sealant or joint filler over cracks or joints where expansion and contraction may occur. For these purposes use *LANCO® Siliconizer Crack Filler™ RC-230*.

Cleanup: Clean all equipment immediately after use with warm soapy water.

Caution: Do not take internally. Keep out of reach of children. Use only with adequate ventilation.

Precaution: Do not apply when temperature is below 40°F (5°C). Apply liberally, but do not overspread. Keep from freezing.

Notice: The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to changes without prior notice.

M.S.D.S.: Available upon request.