



Concrete Seal Plus™ CC-802

Sealant for Joints and Floors

Description:

Concrete Seal Plus™ is a urethane and silicon elastomeric sealant, of good adhesion on concrete to seal cracks on floors, sidewalks, and more. Formulated to be resistant to oil, fuel, grease, and salt.

Product Advantages:

- High adhesion to concrete.
- Can be painted.
- Mildew and UV resistant.
- To seal joints and seams.
- To seal joints and cracks on concrete floors.
- Seals and waterproofs.
- Cleans with water.
- For interior & exterior.

Uses:

Concrete Seal Plus™ is designed to seal and waterproof cracks, holes and joints, in interiors & exteriors. It can also be used as a filler between different types of concrete.

Adheres to painted or unpainted surfaces:

- Concrete
- Fiber cement panels
- Moldings

For use to seal cracks in:

- Porches
- Sidewalks
- Garage floors
- Bases on level ground

Coverage:

Joint size in inches.

Width	Depth	
	Inch	
3/4"	1/4"	24.8'
	1/2"	12.4'
	3/4"	8.1'
	1"	6.1'

Linear feet of sealant per 10.1 fl.oz.

Product Data:

Product Type:	Urethane Silicon Resin
Finish color:	Ultra White
Solids (%):	74 ± 3 by weight 61 ± 3 by volume
Weight/Gallon:	12.75 lb ± 0.05 (5.782 kg ± .02)
Drying time:	12-15 minutes
Tack free:	24 hours
Final Cure:	
Sizes:	10.1 fl.oz. cartridge
Viscosity:	340,000 - 380,000 cp
Percent Pigment by weight:	52 ± 3%
VOC:	<100 g/L

Notice: The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.

F.D.S.: Available upon request.

Application Method:

For best results, follow these steps:

1. Surface must be free of dust, dirt and grease. Remove all loose sealant.
2. Apply at temperatures above 40°F (5°C) when no precipitation is expected for 72 hours.
3. Cut nozzle to desired bead size (1/4" is recommended).
4. Hold gun at a 45° degree angle to the seam push Concrete Seal Plus™ CC-802 ahead of nozzle, applying uniform pressure to the trigger in order to get a smooth bead.
5. Within 15 minute tool with protected finger or smooth sponge.
6. Limit joint size to be filled to approximately 1/4" (0.64 cm) in depth and 1/4" (0.64 cm) in width. If depth of joint exceeds 3/8" (0.96 cm), use polyethylene foam or oakum as backup filler.
7. Wipe away excess with a damp cloth before surface skins.
8. Wait 2 hours before painting with latex paint, 24 hours if using alkyd (oil) based paint.

Surface Preparation:

The surface and edges of the joint must be sound, clean, dry and free of oil, grease or other contaminants that may prevent adhesion.

Mildewed surfaces: Any existing mildew on the surface must be completely killed and removed prior to the application of new caulk. Using a long-handled brush, scrub mildewed surface with Drycoat Cleaner. Rinse thoroughly and let dry completely.

Previously caulked surfaces: It is critical to remove as much old sealant as possible before applying new caulk, especially if it is cracked, eroded or pulled away from the joint.

Additional Label Information :

Cleanup: Clean up excess with damp cloth before caulk cures.

Storage: Protect from freezing; store in a cool, dry place at room temperature. Product must be used within one year of purchase.

Note: Not recommended for use on horizontal surfaces where water may collect, or for marine use areas below water grade level.

40-Year Limited Warranty: Satisfaction guaranteed. If product cracks, peels or separates during period of guarantee when used as directed, return sales receipt and used container to Lanco® Mfg. Corp. for product replacement. The seller will not accept liability for more than product replacement or purchase price.

Danger/Warning:

Use only with adequate ventilation. Ventilation must be sufficient to limit exposure below F.D.S. limits.

Caution: Flammable vapors may cause flash fire. Before applying, extinguish pilot lights, shut off electrically operated appliances and eliminate other sources of flame or sparks and leave off until area is clear of vapors. Do not smoke. Close container tightly after each use. Provide adequate ventilation during application and drying cycle.

Warning! Keep out of reach of children. Do not take internally. For chemical emergency call ChemTrec 1-800-424-9300 (USA) or 1-703-527-3887 (International).

Limitations & more information:

Read Safety Data prior to use.

Go to www.lancopaints.com.

Protect from freezing.

