



Contact Cement CA-152 • CA-153

Spray Industrial Strength Contact Adhesive

Description:

Contact Cement CA-152 • CA-153 is an industrial grade contact cement, formulated with solvent based chloroprene rubber, for decorative laminates in natural or red color. Spray-grade rubber in a volatile solvent that resists water, heat, oil, grease and most chemical.

Product Advantages:

- Self-curing and air-drying
- Spray grade
- Fast dry
- Permanent bond
- Resistant to heat, water and oil
- Resists most chemicals
- Up to 30 minutes to work it.

Uses:

For industrial and construction use only, to bond decorative laminates, countertops, wood canvas, plywood, formica and many other similar and dissimilar materials.

Adheres to porous and non-porous surfaces:

- Wood
- Plywood
- Leather
- Synthetic rubber
- Decorative laminates
- Countertops

Surface Preparation:

All surfaces to be bonded must be clean, dry and free of contaminants such as dirt, oil and grease films.

Product Data:

| | |
|----------------|---|
| Product Type: | Chloroprene Rubber |
| Finish Color: | Natural (CA-152) Red (CA-153) |
| Solids (%): | 18 ± 2% by weight 12 ± 2% by volume |
| Weight/Gallon: | 6.64 ± 0.05 lbs. (3.00 ± 0.02 kg.) |
| Open Time: | Up to 30 minutes |
| Drying Time: | 10-15 minutes |
| Sizes: | 55 gallons 5 gallon |
| Viscosity: | 250-300 CPS |
| Flash Point: | < 20°F TCC |
| Coverage: | 200 ft. ² /gal. (18 m ² /gal.) |

Notice: The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.

S.D.S.: Available upon request.

Storage:

Protect from freezing; store in a cool, dry place at room temperature. Product must be used within one year of purchase.

Application Method:

For best results, follow these steps:

1. Stir thoroughly. Apply at temperatures above 65°F (18°C).
2. Surfaces must be clean, dry and free from loose or foreign matter.
3. Apply Lanco® Contact Cement to both surfaces and allow ten to fifteen minutes to dry. Avoid excessive drying.
4. Align parts exactly before pressing surfaces together; repositioning is impossible once contact is made.
5. Press parts firmly together by hand or mechanical roller.
6. Keep container tightly closed when contact cement is not in use. Avoid storage at temperatures above 100°F (38°C) or over six months.

Danger / Warning:

Use only with adequate ventilation. Ventilation must be sufficient to limit exposure below S.D.S. limits.

Limitation: This product must not be used in any fully constructed home or non-industrial building.

Caution: Contains petroleum distillates, acetone, toluene, M.E.K. (Methyl Ethyl Ketone), heptane and hexane. Flammable vapors may cause flash fire. Before applying, extinguish pilot lights, shut off electrically operated appliances and eliminate other sources of flame or sparks and leave off until area is clear of vapors. Do not smoke. Close container tightly after each use. Provide adequate ventilation during application and drying cycle.

Warning!: Keep out of reach of children. Do not take internally.

For chemical emergency call ChemTrec 1-800-424-9300 (USA) or 1-703-527-3887 (International).

Limitations & more information:

Read Safety Data Sheet prior to use.

Go to www.lancopaints.com.

Protect from freezing.

