



# Bonding Agent 45% CB-950 • CB-951

## Re-Wettable Concrete Bonder

### Description:

**Bonding Agent CB-950 • CB-951** is a concrete bonding adhesive for interior or exterior plastering or plastering mix. This thick homopolymers emulsion is used to bond new to old concrete, thick concrete and roof ceilings plaster without a laborious scarification process. It will add resiliency and toughness when used as an additive for applications in cement to cement, cement to wood, plaster, stucco, tile and plaster to plaster.

### Product Advantages:

- In color blue or white
- For thick and roof ceilings plaster
- Excellent bond strength
- Fast drying
- Permanent bond
- Water and humidity resistant
- Meets ASTM C-631 & ASTM C-932
- To apply or mix with the plaster cement

### Uses:

For industrial and construction use only, to provide a permanent bond between the cement plaster mix and structurally sound substrates.

Adheres to porous and non-porous surfaces:

- Wood
- Concrete
- Old or existing plaster
- Wallboard
- Interior roof ceilings
- Lime plaster

### Surface Preparation:

All surfaces to be bonded must be clean, dry and free of contaminants such as dust, sand, oil and grease films.

### Product Data:

Product Type:	Homopolymers Emulsion
Finish color:	Blue CB-950 White CB-951
Solids (%):	45 ± 2% by weight 40 ± 2% by volume
Weight/Gallon:	9.24 ± 0.05lbs. (4.19 ± 0.02kg.)
Drying time:	20-30 minutes
Sizes:	55 gallons 5 gallons 1 gallon
Thinning:	Is not recommended
Viscosity:	2600 - 2700 CPS
Flash Point:	Non-flammable
Coverage	250 ft. <sup>2</sup> /gal. (29.7 m <sup>2</sup> /gal.)
VOC:	<50 G/l

Notice: The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.

S.D.S.: Available upon request.

### Product Information:

**Storage:** Protect from freezing; store in a cool, dry place at room temperature. Product must be used within one year of purchase.

**Mixing:** Always mix thoroughly by hand or with a power agitator before application.

**Cleanup:** Clean all equipment immediately after use with warm soapy water. Completely flush all spray equipment with this solution.

### Method of Application:

For satisfactory bonding, follow the procedure:

1. Stir contents of container thoroughly before use. Do not dilute to make volume.
2. Surface should be free of dust, sand or foreign matter.
3. Apply a uniform coat to the surface by brush, roller or spray gun.
4. Before applying the concrete plaster, check surface for uniformity of color. Areas that are irregular in shade indicate an insufficient amount of bonding has been applied.
5. Allow at least two hours for bonding to cure before applying concrete plaster.
6. If cured 24 hours, apply an additional coat before applying concrete plaster.
7. Always maintain the proper level of water in the concrete plaster mix. Do not apply too dry.
8. When troweling the concrete plaster, use a circular motion follow through on all strokes. Never pull the trowel away perpendicular to the surface.

### Danger/Warning :

Use only with adequate ventilation. Ventilation must be sufficient to limit exposure below S.D.S. limits. Do not apply when temperature is below 40° F (5° C). Keep from freezing.

**Warning!** Keep out of reach of children. Do not take internally.

For chemical emergency call ChemTrec 1-800-424-9300 (USA) or 1-703-527-3887 (International).

### Limitations & more information:

Read Safety Data Sheet prior to use. Go to [www.lancopaints.com](http://www.lancopaints.com). Protect from freezing.



- 
- **NORTH AMERICA** • 600 Mid Florida Drive Airport Industrial Park of Orlando, Florida 32824 • Tel. (407) 240-4000 Fax (407) 240-4046
  - **CARIBBEAN & SOUTH AMERICA** • Urb. Aponte #5, San Lorenzo, Puerto Rico USA 00754 • Tel. (787) 736-4221 Fax (787) 736-5313
  - **CENTRAL AMERICA** • Zona Industrial Bes, lote #4, El Coyol de Alajuela, Costa Rica • Tel. (506) 2438-2257 Fax (506) 2438-2162