



TECHNICAL DATA SHEET

Complete ZERO (JB-490)

Professional Interior Zero VOC Semi-Gloss Paint

Description	Technical Data	Application				
<p>Lanco® Complete™ Zero is a professional quality interior zero VOC semi-gloss paint for new or previously painted substrates designed for professional applicators. Complete ZERO™ is a very low odor, zero VOC paint with all the desirable characteristics of a premium quality paint. It dries in 1 hour and presents an extremely durable film that resists yellowing, chipping, cracking and peeling. May be applied with brush, roller or spray.</p>	<p>SOLIDS: 53.2 ± 1% by weight 39.9 ± 1% by volume</p> <p>V.O.C LEVEL less than 5 g/L</p> <p>WEIGHT / GALLON: 10.55± 0.2 lbs.</p> <p>FINISH: Semi- gloss (40°-50°) *Geometry 60°</p> <p>FLASH POINT: Non-flammable</p> <p>FIRE RATING: Class A</p> <p>VISCOSITY: 98-105 Ku's</p> <p>SUGGESTED FILM THICKNESS, COVERAGE PER COAT: 4.0 mils wet, 1.6 mils dry 375-425 sq ft/ gal</p> <p>*Coverage figures do not include surface porosity, irregularities & material loss due to application methods.</p>	<p>Stir or shake thoroughly before using. Read all label and Safety Data Sheets (S.D.S.) information prior to use. Paint always on shaded side of the building. Do not apply in cold, damp conditions. Avoid exterior application late in the day when dew or condensation is likely to form or rain is expected. Typical standard practice recommends intermixing when working with more than one container of a tinted color, to ensure color consistency.</p> <p>BRUSH: Use a high quality nylon or polyester brush.</p> <p>ROLLER: Use a ½" to 1 ¼" nap roller cover, depending on the substrate texture.</p> <p>AIRLESS SPRAY: Use a tip size from .017" to .023". Spray application must be back rolled to work material into surface.</p> <p>MIXING: Always mix thoroughly before and during application.</p> <p>THINNING: This product is not to be thinned.</p> <p>CLEANUP: Clean all equipment immediately after use with warm soapy water. Completely flush all spray equipment with this solution.</p> <p>DRYING TIME@ 77°F @ 50% RH: Temperature and humidity dependent. To touch: 1 hour To recoat: 4 hours</p>				
<p>Product Advantages</p> <ul style="list-style-type: none">• Zero VOC• Mildew and stain resistant• Easy to clean• Variety of color• Excellent coverage• Washable						
<p>Product Uses</p> <p>Interior Surfaces: Ideal for use in occupied areas such as: hotel/motel, resort properties, nursing homes, homes, schools, government facilities, retail space, office buildings, hospitals and apartments. Used on new or previously coated drywall, plaster, acoustical tile, concrete, cement block, wood trim & doors, steel and aluminum.</p>	<p>Recommended Systems</p> <p>SUBSTRATE:</p> <p>Plaster: 1 ct. Prepare Primer Line (HB, L5 or Zero) 2 ct. Complete Zero Professional Finish</p> <p>Gypsum / Drywall: 1 ct. Prepare Primer Line (HB, L5 or Zero) 2 ct. Complete Zero Professional Finish</p> <p>Wood: 1 ct. Prepare Primer Line (HB, L5 or Zero) 2 ct. Complete Zero Professional Finish</p> <p>Metal, Steel: 1 ct. Ultra Durex Primer or MM Oxide Primer 2 ct. Complete Zero Professional Finish</p> <p>Galvanized: 1 ct. Ultra Durex Primer 2 ct. Complete Zero Professional Finish</p> <p>Other Primers may be used upon job inspection.</p>					
<p>Base & Tinting Information</p> <p>Follow tinting requirement specified within appropriate color formula book, color matching computer and automatic tinting equipment.</p> <p>BASE/COLOR: JB-490 White /Pastel</p>						
<p>The use of deep tinted colors or high contrast accent colors may require the addition of one or more finish to achieve acceptable coverage and hiding results.</p>						
		<p>Technical Compliance:</p> <table border="1"><tr><td>AIM:</td><td>PASSES</td></tr><tr><td>OTC:</td><td>PASSES</td></tr></table>	AIM:	PASSES	OTC:	PASSES
AIM:	PASSES					
OTC:	PASSES					

Surface Preparation

Surface must be completely dry and in sound condition. All surfaces must be clean and free of contaminants such as form and release agents, dirt, grease, oil, rust, chalk, efflorescence, organic growth, mildew and non-adherent material. Gloss finishes should be sanded or de-glossed. Feather sand rough edges and spot prime bare areas. Any deteriorated or failed sealant and/or patching compound should be removed and replaced. Fill cracks and primed nail holes with spackling compound and let dry two hours before painting.

PLASTER SURFACES: Plaster nibs should be scraped and sanded smooth. Cracks should be filled with LANCO® Vinyl/Acrylic Spackling Compound SC-101 and let dry two hours before painting. No paint or sealer should be applied on plaster when the moisture content exceeds 8%, as determined by a reliable electronic moisture meter. Use Lanco® Prepare™ Primers.

GYPNUM WALLBOARD SURFACES: Tape and smooth joints with LANCO® Spackling Compound SC-101 and let dry for two hours. Use Lanco® Prepare™ Primers.

WOOD: Caulk primed nail heads and joints or cracks with LANCO® Ultrathane WB™ and allow to dry 24 hours before painting. Sand rough areas, and prime entire surface with LANCO® Titanium Primer™

STEEL AND ALUMINUM: Remove rust by hand or power tool cleaning (SSPC-SP 2-63 or SP 3-63) and prime with LANCO® Ultra Durex Primer™ or LANCO® Metal Master Primer™.

PREVIOUSLY PAINTED SURFACES:

SURFACES IN GOOD CONDITION: Sand any glossy areas by brush blasting (SSPC-SP 7-63) and dust clean.

SURFACES IN POOR CONDITION: If paint is old, loose, peeling or badly weathered, repair and clean surface by sanding, brush blasting (SSPC-SP 7-63) or other methods in order to provide a sound surface. Apply a full coat of primer as recommended.

MILDEWED SURFACES: Any existing mildew on the surface must be killed and removed prior to the application of this product. Any mildew not removed may continue to grow through the new finish. Using a long-handled brush, scrub mildewed surfaces with a mixture of one quart of household bleach and three quarts of warm water. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach / water solution.

General Information

PRECAUTION: For interior use only. Do not add mineral spirits or other solvents to this product. Do not apply when surfaces or air temperature are below 50°F (10°C). Do not expose to freezing temperatures in storage. Do not use on unpainted ferrous metal. Do not use on staining wood such as cedar, mahogany, or redwood.

LIMITED WARRANTY: The manufacturers liability in connection with the sale of this product extend only to the replacement price if it should fail to comply with quality standards or specifications.

CAUTION: Harmful if swallowed. Contains Acrylic Resin. In case of eye contact, flush thoroughly with water. Do not rub eyes. In case of skin contact, flush area immediately with clean water. If swallowed, do not induce vomiting. Consult a physician immediately. Use only with adequate ventilation. Adequate ventilation required when sanding or abrading the dried film. Always use NIOSH/MSHA TC21C or equivalent.) Goggles are recommended while handling the product. Keep out of reach of children.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. For chemical emergency call ChemTrec 1-800-424-9300. PROTECT FROM FREEZING.

S.D.S.: Available upon request.

The information presented on this Technical Data Sheet is based on testing conducted by Lanco® Paints & Coatings. No guarantee of accuracy, comprehensiveness, or performance is given or implied. Information and recommendations are subject to change dependent on surface conditions (substrate), weather and method of application. Please consult with a Lanco Representative or visit www.lancopaints.com for complete, up-to-date technical information.



- **NORTH AMERICA** • 600 Mid Florida Drive Airport Industrial Park of Orlando, Florida 32824 • Tel. (407) 240-4000 Fax (407) 240-4046
- **CARIBBEAN & SOUTH AMERICA** • Urb. Aponte #5, San Lorenzo, Puerto Rico USA 00754 • Tel. (787) 736-4221 Fax (787) 736-5313
- **CENTRAL AMERICA** • Zona Industrial Bes, lote #4, El Coyol de Alajuela, Costa Rica • Tel. (506) 2438-2257 Fax (506) 2438-2162